

SPECIAL NOTES

NOTE 'A' : LOW STRENGTH MORTAR BACKFILL (LSMB)

WHEN USING LOW STRENGTH MORTAR BACKFILL (LSMB), THE OPTIONAL FILL AREA OVER THE CONDUIT MAY BE BACKFILLED WITH SAND, GRANULAR MATERIAL, OR OTHER SUITABLE 912 MATERIAL, FOR A DISTANCE NOT TO EXCEED 1 FT. A PROTECTIVE BARRIER OF VISQUEEN OR SIMILAR MATERIAL IS PERMITTED.

NOTE 'B' : TYPE 1 PAVEMENT REPAIR SEALING

FOR TYPE I PAVEMENT REPAIR SEALING OPTIONS - THE FOLLOWING METHODS ARE PERMITTED:

1. CRACK SEALING METHOD: SEAL THE PERIMETER SURFACE OF THE REPAIRED AREA BY APPLYING A NOMINAL 4 INCH STRIP OF APPROVED ITEM 423 - CRACK SEALING, TYPE II OR III.
2. HEAT WELD METHOD: FOR PAVEMENT REPAIR LOCATIONS, THE AREA TO BE HEAT WELDED IS TO INCLUDE THE CUT AND EXTEND FOR 6 INCHES BEYOND EACH SIDE OF THE CUT FOR A NOMINAL DEPTH OF 2 INCHES.

NOTE 'C' : TYPE 1 PAVEMENT REPAIR RESURFACING (SEE SHEETS 9-11)

FOR TYPE I PAVEMENT REPAIR APPLICATIONS, THE FOLLOWING METHODS ARE PERMITTED:

1. IF LANE WIDTH TO BE RESURFACED: USE ITEM 441 ASPHALT CONCRETE, INTERMEDIATE COURSE, TYPE 2, (BINDER MATCHING SURFACE COURSE) PLACED IN LIFTS NOT EXCEEDING 3 INCHES TO REPAIR PAVEMENT TO THE SURFACE. DURING THE LATER MILL AND ASPHALT OVERLAY OPERATION, USE ITEM 441 ASPHALT CONCRETE SURFACE COURSE, TYPE 1.
2. IF NO LANE WIDTH RESURFACING: USE ITEM 441 ASPHALT CONCRETE, INTERMEDIATE COURSE, TYPE 2, PLACED IN LIFTS NOT EXCEEDING 3 INCHES AND ITEM 441 ASPHALT CONCRETE, SURFACE COURSE, TYPE 1 PLACED AT A MAXIMUM 1.5 INCH LIFT THICKNESS. THE INTERMEDIATE COURSE MATERIAL IS NOT PERMITTED AS THE FINAL SURFACE COURSE.

THE ASPHALT BINDER FOR INTERMEDIATE AND SURFACE COURSE ASPHALT SHALL BE PG 70-22 ON ARTERIAL ROADWAYS, BUS ROUTES, AND WHERE SPECIFIED BY THE PERMIT OFFICE. ALL OTHER ROADS SHALL BE PG 64-22.

TRENCHES THAT REQUIRE FULL LANE RESURFACING SHALL INCLUDE FULL LANE RESURFACING ON ALL CONNECTING TRENCHES AND ASSOCIATED VALVE OR CASTING WORK AREAS ALONG ADJACENT STREETS (UTILITY SERVICE REPAIRS SHALL BE AS PER SHEETS 9, 10 AND 11.) REGARDLESS OF THE LENGTH OF THE CONNECTING TRENCH.

WHEN AN EXCAVATION EXCEEDS 100 FT IN LENGTH, THE REPAIR SHALL INCLUDE ITEM 254 PLANING OF A FULL LANE WIDTH (OR ANY OTHER LANE WIDTH AS DIRECTED BY THE DEPARTMENT OF PUBLIC SERVICE) TO A DEPTH OF 1- 1/2 INCHES FOR THE ENTIRE LENGTH OF THE EXCAVATION. THE RESURFACING SHALL NOT INTRODUCE ANY LONGITUDINAL PAVEMENT JOINTS. WHEN RESURFACING OUTSIDE LANES, RESURFACING SHALL EXTEND TO THE FACE OF CURB OR EDGE OF PAVEMENT. IF PAVEMENT PLANING DOES NOT PROVIDE A UNIFORM PLANED SURFACE DUE TO THE EXISTING PAVEMENT CONDITION, THE DEPTH OF THE PAVEMENT REMOVAL AND RESURFACING SHALL BE ADJUSTED ACCORDINGLY. WHERE THE PROPOSED RESURFACING IS IN CLOSE PROXIMITY TO AN EXISTING LONGITUDINAL JOINT, THE RESURFACING SHALL BE EXTENDED TO MEET OR OVERLAP THAT JOINT. WHEN RESURFACING ADJOINS AN AREA WITH EXISTING OVERLAID GUTTER, THE RESURFACING SHALL EXTEND THE FULL LANE WIDTH TO THE EXISTING PAVEMENT EDGE AT THE FACE OF CURB. THE PLANED AREA SHALL BE TACKED USING ITEM 407.02 MATERIAL PRIOR TO PLACING AND COMPACTING APPROVED ASPHALT CONCRETE WITH A PAVER IN ACCORDANCE WITH CURRENT CITY STANDARD SPECIFICATIONS. ITEM 423 -CRACK SEALING, TYPE II OR III SHALL BE APPLIED TO EXPOSED JOINTS ONCE THE PAVING OPERATION HAS BEEN COMPLETED.

PAVEMENT & UTILITY CUT REPAIR STANDARDS

CITY OF COLUMBUS, OHIO
DEPARTMENT OF PUBLIC SERVICE
DIVISION OF DESIGN AND CONSTRUCTION

STD DWG

1441

07/01/2021

SHT 5 OF 13